

L9 ANSWER 18 OF 29 CAPLUS COPYRIGHT 2003 ACS on STN

ACCESSION NUMBER: 1974:554485 CAPLUS

DOCUMENT NUMBER: 81:154485

TITLE: Water- and oil-repelling products for wet treating of  
fibers

INVENTOR(S): Iwatani, Akitoshi

PATENT ASSIGNEE(S): Daikin Kogyo Co., Ltd.

SOURCE: Jpn. Kokai Tokkyo Koho, 6 pp.

CODEN: JKXXAF

DOCUMENT TYPE: Patent

LANGUAGE: Japanese

FAMILY ACC. NUM. COUNT: 1

PATENT INFORMATION:

PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
JP 48023684	A2	19730327	JP 1971-57824	19710730
PRIORITY APPLN. INFO.:			JP 1971-57824	19710730

AB Maleic anhydride and (or) maleic acid (I) [110-16-7] are added to an aq. dispersion of a copolymer with C3-21 fluoroalkyl pendant groups derived from CH<sub>2</sub>:CRCO<sub>2</sub>CH<sub>2</sub>CH(O<sub>2</sub>CR<sub>1</sub>)CH<sub>2</sub>R<sub>2</sub> (R = H or Me, R<sub>1</sub> = C<sub>1</sub>-17 alkyl, R<sub>2</sub> = perfluoroalkyl) and \*\*\*acrylic\*\*\* acid, methacrylic acid, and (or) their esters to give a water- and oil-repellent agent. Thus, a nylon textile was immersed in an \*\*\*emulsion\*\*\* contg. 0.5 wt. % I and 0.5 wt. % 2-ethylhexyl methacrylate-N-methylolacrylamide-3-[7-(trifluoromethyl)perfluorooctyl]-2-acetoxypentyl \*\*\*acrylate\*\*\* copolymer [ \*\*\*52830-82-7\*\*\* ], squeezed to 50% pickup, dried 10 min at 88.deg., and heated 3 min at 140.deg.. The textile had water repellency (JIS L 1004-22) 80 and oil repellency (AATCC 118-66T) 7.

EV979440213